

ATP®-924x

High-Temperature Protective Coating For Steel 不锈钢高温防护涂层

Description 描述

A water-based high-temperature protective coating to control the formation of oxide scale tool and stainless steels.

这是一款专为工具钢及不锈钢定制的水基高温防护涂层,旨在高效抑制其表面氧化皮的形成

• Performance Characteristics 性能特征

- ➤ effective temperature range1700-2300° F (927-1260° C) 有效温度范围 1700-2300° F (927-1260° C)
- retards the formation of oxide scale 高效抑制氧化皮的形成
- exceptional insulating properties and thermal stability 卓越的保温性能与热稳定性
- ▶ demonstrates heat retention properties for improved performance in hot working operations 优良的保温性以提高热加工操作的性能
- > outstanding coverage & performance in one coat 单次涂覆即可实现卓越的覆盖性能
- demonstrates exceptional green strength upon proper drying to withstand cracking, chipping, and peeling

在适当的干燥条件下,具有良好的生坯强度,能够承受开裂、切削、剥落等

- provides excellent rheological properties for dipping and spaying applications 为浸涂和喷涂提供优良的流变性能
- coating can be diluted with water to obtain desired spray viscosity do not over-thin coating 涂料可以用水稀释以获得所需的喷射粘度,切勿过度稀释

• Recommendations for Use使用指导

- thoroughly suspend and mix before use
 - 使用前充分搅拌均匀
- > metal surfaces must be free of dirt, oil, grease, metal oxides, and other materials 金属表面不得有污垢、油污、金属氧化物或其它物质
- coating thickness depends on the time and temperature of exposure (generally, the higher the temperature and longer exposure, the thicker the coating should be applied)
 - 涂层厚度取决于暴露时间和温度(一般温度越高,暴露时间越长,涂层越厚)



a wet film thickness of 5±2 mil should be optimal

最佳湿膜厚度为 5±2 mil

> ensure bottom coat is thoroughly dried when applying multiple coats

多层涂覆时,应确保底层完全干燥

water-based coatings need ample time to completely dry before entering furnace (can be applied over preheated substrate to accelerate drying time)

水基涂料需完全干燥后方可入炉(可涂覆于预热后的基材上以加速干燥)

● Typical Properties 典型属性

% Solids 固体含量	55.0-60.0
Vehicle 溶剂	Water 水
Viscosity (@ 25°C) as Supplied 粘度(CPS)	2000-3000
Weight/Gallon (lbs) 重量 (磅/加仑)	11.85 ± 0.25
Specific Gravity 比重	1.40-1.45
Color 颜色	White 白色
Shelf Life 有效期	2 years 年

• Product Safety 产品安全

Before handling the materials listed in this bulletin, read and understand the product SDS (Safety Data Sheet) for additional information on personal protective equipment and for safety, health, and environmental information.

在处理本公告所列材料前,应阅读并了解 SDS (安全数据表)以获得关于个人防护装备、安全、健康和环境信息等额外信息。

No chemical should be used as or in a food, drug, medical device, or cosmetic, or in a product or process in which it may contact a food, drug, medical device, or cosmetic until the user has determined the suitability and legality of the use. Since government regulations and use conditions are subject to change, it is the user's responsibility to determine that this information is appropriate and suitable under current, applicable laws and regulations.

在用户确定其使用的适用性和合法性之前,本产品不应作为食品、药品、医疗器械或化妆品使用,也不应在任何可能与食品、药品、医疗器械或化妆品接触的产品或工艺中使用。由于政府法规和使用条件可能会发生变化,用户有责任确定该信息是否适用当前的法律法规。

Wuxi Yura Aviation Power Co., Ltd requests that the customer read, understand, and comply with the information contained in this publication and the current SDS(s). The customer should furnish the information in this publication to its employees, contractors, and customers, or any other users of the product(s), and request that they do the same.

无锡优航动力科技有限公司要求客户应阅读、理解并遵守上述信息和最新版本的 SDS(S)。客户应向其雇员、承包商及其客户,或任何其它该产品的用户提供本公告中的信息,并要求他们同样遵守。

• Storage and Handling 存储及处理

ATP®-924x should be stored indoors in the original unopened and undamaged container, in a dry place at a temperature not exceeding 40° C. Exposure to direct sunlight should be avoided.



ATP®-924x 应存放于室内,保持原包装未开封且完好无损,存放环境需干燥且温度不超过 40°C,应避免阳光直射。

IMPORTANT: The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Wuxi Yura Aviation Power Co., Ltd expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated any may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

For further information and more product details, packaging and safety data sheets, contact us as below: 欲了解更多产品信息、包装和安全数据表,请与我们联系

商务合作请联系:	无锡优航动力科技有限公司
	Wuxi Yura Aviation Power Co., Ltd
全国统一热线:	86-510-88270899
办公地址 1:	无锡市新吴区净慧东道 66 号
办公地址 2:	无锡市滨湖区经开区金融八街联合金融大厦 1201 室
仓库地址:	无锡市新吴区干城路 6 号中关村科创园区 43-A 栋
邮箱:	lili.wan@yura-aviation-power.com
网址:	www.yura-aviation-power.com